WSGL Weingarten, Schurgin, Gagnebin & Lebovici LLP

Intellectual Property Law Patents • Trademarks • Copyrights

Ten Post Office Square Boston, Massachusetts 02109 Tel. 617.542.2290 • Fax. 617, 451.0313 www.wsglip.com

RECEIVED CENTRAL FAX CENTER DEC 1 4 2004

FACSIMILE COVER SHEET

DATE:

December 14, 2004

TO: Examiner Ing-Hour Lin

TC Art Unit: 1725

FROM:

Charles L. Gagnebin III

No. of pages transmitted

Fax No.: (703) 872 9306

(including this page):

Our File:

AK-N-421XX

Time: 2:45

Your Ref:

Application No. 10/645,347 Filed Date: August 21, 2003 Confirmation No.: 6740

Sent by:

A confirmation copy of this transmission will not be mailed unless the following is checked: [] **MESSAGE**

> PLEASE DELIVER DIRECTLY TO: EXAMINER ING-HOUR LIN, Tel. (571) 272-1180 TC ART UNIT NO: 1725

FOR ENTRY

Enclosed for filing please find a: STATEMENT OF SUBSTANCE INTERVIEW

The Commissioner is hereby authorized to Charge Deposit Account No. 23-0804 for any additional filing fees associated with this communication or credit any overpayment

> Attorney for Applicant: Charles L Gagnebin III Registration No. 25,467

CLG:mcs/314879-1

THIS MESSAGE MAY CONTAIN CONFIDENTIAL OR PRIVILEGED INFORMATION INTENDED ONLY FOR THE PERSON(S) IDENTIFIED ABOVE. IF IT HAS BEEN RECEIVED AT ANY OTHER PLACE OR HAS NOT BEEN CLEARLY RECEIVED, PLEASE CALL THE ABOVE IDENTIFIED SENDING PARTY COLLECT FOR INSTRUCTIONS. DO NOT SHOW OR DISTRIBUTE THIS MESSAGE TO ANYONE OTHER THAN THE INTENDED RECTPIENT(S). THANK YOU.

PATENT

Rev 06/04

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

Notice of Allowance dated: November 17, 2004

Confirmation No. 6740

In re application

: Atsushi Koide et al.

Application No.

10/645,347

Filed

: August 21, 2003

Confirmation No.

6740

For

COMPOSITE METAL PRODUCT OF CARBON NANO MATERIAL AND LOW MELTING POINT METAL AND

METHOD OF PRODUCING THE SAME

Examiner

Ing-Hour Lin

Attorney's Docket :

AK-N-421XX

TC Art Unit: 1725

Bv:

Charles L. Gagnebin Registration No. 25,467 Attorney for Applicants

STATEMENT OF SUBSTANCE OF INTERVIEW

Via Facsimile Commissioner for Patents P.O. Box 1450 Alexandria, VA 22313-1450

Sir:

In response to the Interview Summary received with the Notice of Allowance dated November 17, 2004, an agreement was reached with the Examiner in a telephone conference discussing claims 1-4 on November 10, 2004, as follows:

WEINGARIEN, SCHURGIN, GAGNEBIN & LEBOVICI LLP TEL, (617) 542-2290 FAX. (617) 451-0313

Application No. 10/645,347 Filed: August 21, 2003 TC Art Unit: 1725

Confirmation No.: 6740

Claims 1-2 were canceled; and Two new dependent claims 5 and 6 were added. The claims now read as follows:

CLAIMS

- (Canceled)
- (Canceled)
- 3. (Previously Presented) A method of producing a composite metal product, comprising the steps of:

injection molding a carbon nano material consisting of a carbon nano tube and a plasticized resin binder to form a preliminarily molded member shaped for a product;

degreasing the preliminarily molded member by heat treatment and forming a preliminarily molded porous member comprising the carbon nano material;

inserting the preliminarily molded porous member into a cavity of a mold shaped for the product;

injecting a molten low melting point metal material into the cavity;

impregnating the preliminarily molded porous member with the low melting point metal material by injection pressure; and

obtaining the composite metal product comprising the low melting point metal material and the carbon nano material integrally composited with.

4. (Previously Presented) The method according to claim 3;

-2**-**

Application No. 10/645,347 Filed: August 21, 2003 TC Art Unit: 1725

Confirmation No.: 6740

wherein the preliminarily molded member is injection molded by a screw type preplasticization injection machine comprising a plasticizing device for plasticizing the carbon nano material and the resin binder and a injection device for injecting the plasticized material, the plasticizing device and the injection device being disposed separately, both the devices are communicated with each other through a flow path, and the plasticized material is injected after metering by the injection device.

- 5. (new) The method according to claim 3, wherein the low melting point metal is a metal or alloys of the metal selected from the group consisting of magnesium (Mg), tin (Sn), aluminum (Al), copper (Cu), lead (Pb), and zinc (Zn).
- 6. (new) The method according to claim 4, wherein the low melting point metal is a metal or alloys of the metal selected from the group consisting of magnesium (Mg), tin (Sn), aluminum (Al), copper (Cu), lead (Pb), and zinc (Zn).

Application No. 10/645,347 Filed: August 21, 2003 TC Art Unit: 1725

Confirmation No.: 6740

REMARKS

The Examiner is encouraged to telephone the undersigned attorney to discuss any matter that would expedite allowance of the present application.

Respectfully submitted,

ATSUSHI KOIDE FT

Charles L. Gagnebin III Registration No. 25,467 Attorney for Applicants

WEINGARTEN, SCHURGIN,
GAGNEBIN & LEBOVICI LLP
Ten Post Office Square
Boston, MA 02109
Telephone: (617) 542-2290

Telephone: (617) 542-2290 Telecopier: (617) 451-0313

CLG:mes/314779-1